

## MoldMAX LH<sup>®</sup>

Materion Brush Performance Alloys' MoldMAX LH (Low Hard) is a premium copper mold alloy that provides hardness and strength comparable with standard AISI P-20 tool steel and a thermal conductivity five-times higher. MoldMAX LH is used for injection mold cores and cavities where moderate hardness and high toughness and conductivity are required.

### CHEMICAL COMPOSITION (weight percent)

Alloy	Beryllium	Cobalt	Copper
MoldMAX LH	1.6 – 2.0	0.2 – 0.3	Balance

### PHYSICAL PROPERTIES

Elastic Modulus	Melting Point (Solidus)	Density	Thermal Expansion	Thermal Conductivity (100 °C)	Heat Capacity (100 °C)
19,000 ksi 131 GPa	~1600 °F ~870 °C	.302 lb/in <sup>3</sup> 8.36 g/cm <sup>3</sup>	9.7x10 <sup>-6</sup> in/in °F 17.5 x 10 <sup>-6</sup> °C <sup>-1</sup>	90 BTU/hr-ft.°F 155 W/m-K	.10 BTU/lb.°F 0.44 J/g-K

### TYPICAL MECHANICAL PROPERTIES\*

0.2% Offset Yield Strength	Ultimate Tensile Strength	Fatigue Strength 10 <sup>7</sup> Cycles (R=I)	Elongation	Impact Strength	Hardness
110 ksi 760 MPa	140 ksi 965 MPa	>45 ksi >310 MPa	15%	15 ft-lb 20 J	30 HRC

\*Properties may vary by shape and thickness.

### FORMS AVAILABLE

Rounds, square and rectangular bars, plate and forged rings.

### RELATED INFORMATION

Additional information on MoldMAX products can be obtained by calling 800-375-4205.

## SAFE HANDLING OF COPPER BERYLLIUM

Handling copper beryllium in solid form poses no special health risk. Like many industrial materials, beryllium-containing materials may pose a health risk if recommended safe handling practices are not followed. Inhalation of airborne beryllium may cause a serious lung disorder in susceptible individuals. The Occupational Safety and Health Administration (OSHA) has set mandatory limits on occupational respiratory exposures. Read and follow the guidance in the Material Safety Data Sheet (MSDS) before working with this material. For additional information on safe handling practices or technical data on copper beryllium, contact Materion Brush Performance Alloys, Technical Service Department at 1-800-375-4205.

### CHINA/HONG KONG

TEL: + (852) 2318-1960 / 1907  
[brushalloysHK-info@materion.com](mailto:brushalloysHK-info@materion.com)

### CHINA/SHANGHAI

TEL: + (86) 21-5237-2328  
[brushalloysCN-info@materion.com](mailto:brushalloysCN-info@materion.com)

### GERMANY

TEL: + (49) 711-830-930  
[brushalloysDE-info@materion.com](mailto:brushalloysDE-info@materion.com)

### INDIA/PUNE

TEL: + (91) 99606-33744  
[brushalloysIN-info@materion.com](mailto:brushalloysIN-info@materion.com)

### JAPAN

TEL: + (81) 33 230 2961  
[brushalloysJP-info@materion.com](mailto:brushalloysJP-info@materion.com)

### REPUBLIC OF KOREA

TEL: + (82) 32-811-2171  
[brushalloysKR-info@materion.com](mailto:brushalloysKR-info@materion.com)

### SINGAPORE/ASEAN

TEL: + (65) 6842-4456  
[brushalloysSG-info@materion.com](mailto:brushalloysSG-info@materion.com)

### TAIWAN, R.O.C.

TEL: + (886) 2-2747-8800 x-121  
[brushalloysTW-info@materion.com](mailto:brushalloysTW-info@materion.com)

### UNITED KINGDOM & IRELAND

TEL: + (44) 118-930-3733  
[brushalloysUK-info@materion.com](mailto:brushalloysUK-info@materion.com)



**Materion Brush Performance Alloys**  
6070 Parkland Boulevard  
Mayfield Heights, OH 44124 USA  
phone: 216.486.4200 fax: 216.383.4005  
email: [alloys-info@materion.com](mailto:alloys-info@materion.com)

### MATERION CORPORATION

[www.materion.com/alloys](http://www.materion.com/alloys)

**AD0059\_0311**

MoldMAX LH® is a Registered Trademark of Materion Brush Inc.  
© 2011 Materion Brush Inc.